

TEST REPORT



REPORT NO. : M270-16-14749
SAMPLE RECEIVED DATE : 2016-12-19
TEST STARTED DATE : 2016-12-19
REPORT ISSUED DATE : 2016-12-23
PAGE : 1 OF 2

DESCRIPTION : ONE(1) PIECE OF SUBMITTED CUTTING SAID TO BE NET.

=====


ITEM : PE SCAFFOLDING NET

=====

TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGES.


=====

PREPARED AND CHECKED BY
FOR FITI



SUNG SIK, KIM
QUALITY MANAGER

AUTHORIZED BY
FOR FITI



YOUNG-CHAN KIM
PRESIDENT

※ Report Verification No.: 1XW5-KFFU-MNYW ※

(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)



01. FLAMMABILITY (NFPA 701 : 2015, TEST METHOD 2(FLAT MATERIAL))

#1

	AS RECEIVED		
	AFTER FLAME TIME(s)	DRIP BURN (s)	CHAR LENGTH (mm)
1	0	0	322
2	0	0	294
3	0	0	317
4	0	0	311
5	0	0	328
6	0	0	308
7	0	0	316
8	0	0	302
9	0	0	309
10	0	0	316
AVG.	0	0	312

NOTE) · CONCLUSION : BASED UPON THE RESULTS OF THE TEST REPORT, THE SUBMITTED SAMPLE MEETS THE PERFORMANCE REQUIREMENTS AS STATED IN NFPA 701, TEST METHOD 2(2015).

· ACCEPTANCE CRITERIA

AFTER FLAME TIME (s)	DRIP BURN (s)	CHAR LENGTH (mm)
MAX. IND. < 2	MAX. IND. < 2	MAX. IND. < 435

· TEST WAS CONDUCTED ONLY IN THE ORIGINAL STATE BY THE CLIENT'S REQUEST.

**** End of The Report ****

SAMPLE :

